

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Create Timber Floor
18 Natalia Avenue
Oakleigh South VIC 3167

Test Number : 25-000321
Issue Date : 13/02/2025
Print Date : 13/02/2025

Sample Description Clients Ref : "Oak Collection"
Engineered timber flooring plank
End Use : Flooring
Nominal Composition : Oak, Multi-ply Core
Nominal Mass per Unit Area/Density : 680kg/m³
Nominal Thickness : 14mm



342432

75265

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved




Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Create Timber Floor
18 Natalia Avenue
Oakleigh South VIC 3167

Test Number : 25-000321
Issue Date : 13/02/2025
Print Date : 13/02/2025

AS 4586-2013 Appendix A

Slip Resistance Classification of new Pedestrian Surface Materials Wet Pendulum Test Method

Date of Testing 13-02-2025
Operator AWTA Test Operator 14
Test Temperature (20±5degC) 21 °C
Specimens Washed with pH Neutral detergent then dried
Test Direction Length
Fixed/Unfixed Unfixed

Slider No 96 Batch No					33	
Length	1	2	3	4	5	SRV
British Pendulum number	37	39	36	40	36	38

Classification P3

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 11/10/2023
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

342432

75265

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR